

AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions, and listings, of claims in the application:

LISTING OF CLAIMS:

1. - 21. (Canceled)

22. (New) A photo-curable resin composition comprising a cationic photopolymerization initiator (A) and a cationically polymerizable compound (B), wherein the component (B) comprises a compound containing an oxetanyl group at a mass ratio of at least 1/1000 of the component (B), and comprises a fluorine-containing organic compound in an amount of over 0% by mass and 40% by mass or less in terms of fluorine atom (B), based on an amount of the component (B).

23. (New) The photo-curable resin composition according to claim 22, further comprising an inorganic filler in an amount of 0 to 250 parts by mass, based on 100 parts by mass of the sum of the components (A) and (B).

24. (New) A photo-curable resin composition comprising a cationic photopolymerization initiator (A), a cationically polymerizable compound (B) and a cyclic polyether compound (C), wherein the component (B) comprises a compound containing an oxetanyl group at a mass ratio of at least 1/1000 of the component (B),

the amount of the component © is 0.3 to 10% by mass, based on the sum of the components (B) and (C), and

at least one of the components (B) and (C) comprise a fluorine-containing organic compound in an amount of 0 to 40% by mass in terms of fluorine atom (F), based on the sum of the components (B) and (C).

25. (New) The photo-curable resin composition according to claim 24, further comprising an inorganic filler in an amount of 0 to 250 parts by mass, based on 100 parts by mass of the sum of the components (A), (B) and (C).

26. (New) A photo-curable resin composition comprising a cationic photopolymerization initiator (A), a cationically polymerizable compound (B) and another organic compound (D),

wherein the component (B) comprises a compound containing an oxetanyl group at a mass ratio of at least 1/1000 of the component (B),

at least one of the components (B) and (D) comprise a fluorine-containing organic compound in an amount of over 0% by mass and 40% by mass or less in terms of fluorine atom (F), based on the sum of the components (B) and (D).

27. (New) The photo-curable resin composition according to claim 26, further comprising an inorganic filler in an amount of 0 to 250 parts by mass, based on 100 parts by mass of the sum of the components (A), (B) and (D).

28. (New) A photo-curable resin composition comprising a cationic photopolymerization initiator (A), a cationically polymerizable compound (B), a cyclic polyether compound (C) and another organic compound (D),

wherein the component (B) comprises a compound containing an oxetanyl group at a mass ratio of at least 1/1000 of the component (B),

the amounts of the components (B) and (C) are 1 to 90% by mass and 0.3 to 10% by mass, respectively, both based on the sum of the components (B), (C) and (D), and

at least one of the components (B), (C) and (D) comprise a fluorine-containing organic compound in an amount of 0 to 40% by mass in terms of fluorine atom (F), based on the sum of the components (B), (C) and (D).

29. (New) The photo-curable resin composition according to claim 28, further comprising an inorganic filler in an amount of 9 to 250 parts by mass, based on 100 parts by mass of the sum of the components (A), (B), (C) and (D).

30. (New) The photo-curable resin composition according to any one of claims 22 to 25, wherein the component (B) contains a fluorine-containing coupling agent.

31. (New) The photo-curable resin composition according to any one of claims 26 to 29, wherein the component(s) (B) and/or (D) contain a fluorine-containing coupling agent.

32. (New) A sealing agent for a flat panel display, comprising the photo-curable resin composition according to any one of claims 22 to 29.

33. (New) A method for sealing a flat panel display using the sealing agent according to claim 32.

34. (New) A flat panel display which is obtained by the method for sealing according to claim 33.